

# STAINLESS TUBES AISI 316L

O.D x W,T	Working pressure Bar		Kg/m
	* 1	* 2	
6 x 1.0	525	2120	0.07
8 x 1.0	379	1514	0.17
8 x 1.5	605	2446	0.24
10 x 1.0	279	1178	0.22
10 x 1.5	467	1871	0.31
10 x 2.0	654	2650	0.40
12 x 1.0	244	964	0.27
12 x 1.5	381	1514	0.39
12 x 2.0	528	2120	0.49
12 x 2.5	680	2789	0.59
15 x 1.5	298	1178	0.50
16 x 1.5	278	1093	0.54
16 x 2.0	382	1514	0.69
16 x 2.5	491	1963	0.83
18 x 1.5	245	964	0.61
18 x 2.0	335	1325	0.79
20 x 2.0	299	1178	0.89
20 x 2.5	382	1514	1.08
20 x 3.0	467	1871	1.26
22 x 1.5	198	776	0.76
22 x 2.0	299	1060	0.99
25 x 1.5	173	677	0.87
25 x 2.0	235	922	1.13
25 x 2.5	299	1178	1.39
25 x 3.0	364	1448	1.63
25 x 4.0	504	2019	2.07
28 x 2.0	208	815	1.28
28 x 2.5	264	1039	1.57
28 x 3.0	321	1272	1.85
30 x 2.0	194	757	1.38
30 x 2.5	246	964	1.70
30 x 3.0	298	1178	2.00
30 x 4.0	410	1631	2.56
35 x 2.0	165	642	1.63
35 x 2.5	209	815	2.00
35 x 3.0	252	994	2.37
38 x 2.5	191	764	2.19
38 x 3.0	231	909	2.59
38 x 4.0	316	1247	3.35
38 x 5.0	404	1606	4.07
42 x 2.0	136	530	1.97
42 x 2.5	177	671	2.43
42 x 3.0	208	815	2.89
42 x 4.0	283	1116	3.75
50 x 3.0	173	677	3.48
50 x 5.0	299	1178	5.55
60 x 3.0	143	588	4.22
60 x 5.0	245	964	6.78
66 x 8.5	392	1669	12.05
80 x 10	379	1514	17.21

\*1 : Bending, and production tolerances included.

\*2 : Burst pressure based on Tensile Value.